

JUTATOP[®] WB

valid from 01.01.2013

Revision 09.09.2020

PROPERTIES	METHOD	UNITS	NOMINAL VALUE	TOLERANCE	
				MINIMUM	MAXIMUM

Informative section:


Length	EN 1848-2	[m]	>50	-	-
Width	EN 1848-2	[m]	*	-0,5%	+1,5%
Straightness	EN 1848-2	-	conforming	-	-
Mass per unit area	EN 1849-2	[g/m ²]	270	-20	+20
Visible defects	EN 1850-2	-	without visible defects		

Normative part:

Reaction to fire	EN 13501 EN 11925-2	[class]	B	-	-
Resistance to water penetration	EN 1928	[class]	W1	-	-
Resistance to water penetration after artificial ageing	EN 13859-2 Annex C	[class]	W1	-	-
Water vapour transmission properties (Sd)	EN 12572	[m]	0,02	-0,01	+0,04
Tensile properties: Maximum tensile force MD / CMD	EN 12311-1 EN 13859-2	[N/50mm]	360 / 240	-60 / -40	+60 / +50
Max tensile force after artificial ageing MD / CMD	EN 13859-2 Annex C	[N/50mm]	350 / 230	-60 / -40	+60 / +50
Tensile properties: Elongation MD / CMD	EN 12311-1 EN 13859-2	[%]	25 / 25	-10 / -10	+15 / +15
Elongation after artificial ageing MD / CMD **	EN 13859-2 Annex C	[%]	23 / 23	-9 / -9	+15 / +15
Resistance to tearing MD / CMD	EN 12310-1 EN 13859-2	[N]	160 / 190	-40 / -50	+50 / +60
Dimensional stability	EN 1107-2	[%]	<1	-	-
Flexibility at low temperature	EN 1109	[°C]	-40	-	-
Resistance to penetration of air	EN 12114 EN 13859-2	[m ³ /(m ² .h.50Pa)]	0	-	-
Temperature Resistance	-	[°C]	-40 / +100	-	-
Hydrostatic pressure test	EN ISO 811	[cm]	>100	-	-
Dangerous substances			npd		

Notes: MD - Machine Direction, CMD - Cross Machine Direction, npd - no performance determined; * - according to requirement; ** - artificial ageing test of UV 5000 h (standart only 336h)

PRODUCT APPLICATION



EN 13859-1:2010 Flexible sheets for waterproofing - Definitions and characteristics of underlays - Part 1: Underlays for discontinuous roofing.
EN 13859-2:2010 Part 2: Underlays for walls

Breather waterproof roofing underlay manufactured from polyester and functional coating, designed for sloping roofs ventilated and unventilated, timber sarking or directly over thermal insulation with recommended overlap and to be used as a wind barrier for vertical or horizontal wall construction. It can be installed directly on thermal insulation. Overlaps should be connected with recommended adhesive tape.